



TECHNICAL SPECIFICATION

Gasket sheet Gambit AF-1000

Material

Gasket sheet **GAMBIT AF-1000** is based on Kevlar® aramide fibres, mineral fibres, and fillers bound with NBR rubber-based binder; reinforced with galvanized steel mesh.

Designation according to DIN 28091-2: FA-AM1-ST

Kevlar® is a registered trademark of E. I. du Pont de Nemours and Company or its affiliates.

General properties and applications

Used in high temperature flange joints, in systems with high fluctuations in pressure and medium flow rate. Features high mechanical resistance. Can be used in automotive industry. It is not recommended with acids and bases. When working with steam mind using suitable mounting clamps. Water, steam, kerosene, gasoline, fuel, and oil resistant.

Admissions / Certificates

Germanischer Lloyd

Maximum working conditions

1	Peak temperature	°C	420
	Temperature under continuous operation	°C	350
	Temperature under continuous operation with steam	°C	250
	Pressure	MPa	12

Dimensions

Standard thicknesses of sheets /thicknesses above 5.0 mm are produced by gluing/	mm	0,8 1,0; 1,5; 2,0; 2,5 3,0; 4,0, 5,0; 6,0	± 0,1 ± 10% ± 10%
Standard dimensions of sheets /custom dimensions available within the total range of 1500x3000 mm/	mm	1500x1500	± 10,0

Non-standard thicknesses and graphiting of sheet surfaces available upon request.

All information in this catalogue is based on years of experience in manufacture and use of the discussed products.

Since sealing performance in the joint is subject to multiple factors such as mounting method, system parameters, and sealed medium, technical parameters specified herein are of informative nature only and cannot be used as grounds for any claims; any special uses of products are subject to consulting with the manufacturer.



Physical and chemical properties

Density		g/cm³	2,2 - 2,45	DIN 28090-2	
Compressibility	typical value	%	9	ASTM F36	
Elastic recovery	min.	%	50	ASTM F36	
Residual stresses 50 MPa/16 h/300 °C/	min.	MPa	32	DIN 52913	
Residual stresses 50 MPa/16 h/175 °C/	min.	MPa	35	DIN 52913	
INCREASE IN THICKNESS					
Oil IRM 903 150 °C/5h	max.	%	8	ASTM F146	
Model fuel B 20 °C/5 h	max.	%	7	ASTM F146	
Kerosene 20 °C/24 h	max.	%	6	ASTM F146	
Colour			graphite		

(Values as detailed in table refer to 2.0 mm thick gasket sheets)



All information in this catalogue is based on years of experience in manufacture and use of the discussed products.

Since sealing performance in the joint is subject to multiple factors such as mounting method, system parameters, and sealed medium, technical parameters specified herein are of informative nature only and cannot be used as grounds for any claims;

any special uses of products are subject to consulting with the manufacturer.